

3000 HT

SUNSHADOW SOLAR SCREEN



TEXTSTYLE



96-D Allen Boulevard
 Farmingdale, New York 11735-5626 USA
 Tel. +1 (631) 293-8944 Fax +1 (631) 293-895
 e-mail: testing@govmark.com

Page 1


Received:08/04/2016	Completed:08/05/2016	Letter: A	BG	P.O.#:	Test Report #:	3-14674-0-
Client's Identification	Style: 3000 HT. Composition: 25% Polyester, 75% PVC. Weight: 12.24 oz/y ² . Thickness: 0.024". End Use: Interior Roller Shades.					
Tested For: Jessica Bondell Rollese Acmeda, Inc. 200 Harvard Avenue Stamford, CT 06902	Key Test: CA 1237 Sm					195
		Tel: 1-(203)-964-1573		Ext:		
		Fax: 1-()- -				
LE: 1993; V 09/15 NTR 04/16 PC: 1H /jd SM/mg						
TEST PERFORMED: California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93) Fire Resistance; Small Scale Test - INTERIOR MATERIALS QUALIFICATION						
RESULTS REPORTED: <input checked="" type="checkbox"/> Initially <input type="checkbox"/> After 3 dry cleanings <input type="checkbox"/> After 5 launderings @ 160°F						
RESULTS:	Specimen #	Afterflame (seconds)	Afterglow (seconds)	Char Length (inches)		
Warp:	1	0	0	4.5		
	2	0	0	4.4		
	3	0	0	4.5		
	4	0	0	4.2		
	5	0	0	4.7		

	Avg:	0				
Fill:	6	0	0	3.9		
	7	0	0	4.0		
	8	0	0	4.5		
	9	0	0	4.4		
	10	0	0	4.2		

	Avg:	0				
APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 12.7 oz/yd ²						
ACCEPTANCE CRITERIA:						
Afterflame:	4.0 seconds maximum average for warp or fill					
Afterglow:	(see Note #2 below)					
Char Length:	6.0 inches maximum for any individual specimen					
NOTES:						
1. An asterisk (*) next to any char length measurement indicates that a part of the char length is melt away due to heat from the flame source and not from propagating flame. Therefore, the sample submitted meets the requirements of Title 19 - California Code of Regulations, Section 1237 and 1237.1 for materials weighing less than 4 oz/yd ² .						
2. Afterglow is required to be reported; however, it is not factored into the Acceptance Criteria.						
(Page 1 of 2)						

3000 HT

SUNSHADOW SOLAR SCREEN



TEXTSTYLE



96-D Allen Boulevard
 Farmingdale, New York 11735-5626 USA
 Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
 e-mail: testing@govmark.com

Page 2

Received:08/04/2016	Completed:08/05/2016	Letter: A	BG	P.O.#:	Test Report #:	3-14674-0-
Client's Identification	Style: 3000 HT. Composition: 25% Polyester, 75% PVC. Weight: 12.24 oz/y ² . Thickness: 0.024". End Use: Interior Roller Shades.					
Tested For: Jessica Bondell	Key Test: CA 1237 Sm					195
Rollease Acmeda, Inc. 200 Harvard Avenue Stamford, CT 06902		Tel: 1-(203)-964-1573		Ext:		
		Fax: 1-() - -				

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

Complies; Does not comply

REMARKS: None.

NOTE: The number of test specimens and Acceptance Criteria are based on a proposed revision issued and implemented by the California State Fire Marshal in August 1993. In substance, the following has occurred:

1. A maximum afterflame of 4 seconds is permitted as opposed to 1 second.
2. It was clarified that the char length maximum of 6 inches applies to any individual specimen and is not an average requirement.
3. Ten specimens are tested in lieu of 6 specimens.

This report issues the conclusion to Section 1237 based on the California State Fire Marshal's continued endorsement of the proposed revision.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

 AUTHORIZED SIGNATURE
 GOVMARK
 /pm/mo

AUG 08 2016

Robert I. Brown

(Page 2 of 2)

The results contained in this report relate only to item(s) tested. The test report shall not be

File Conv